

SARCO GLAZING COMPOUNDS

Frequently Asked Questions

- 1. What's the difference between Dual Glaze and TYPE M?** Dual glaze can be used indoors and outdoors on both wood and metal sash. TYPE M should only be applied indoors and only on wood sash.
- 2. What is the coverage?** For ½" sash approximately 6 feet glazing for 1 lb. of putty.
- 3. Is it advisable to prime the sash before puttying?** Yes. Regardless of whether you're working on wood or metal sash, always prime first. Oil based primer is preferred.
- 4. It is advisable to prime the putty before painting?** No. Do not prime putty. Only use good quality paint.
- 5. How long after applying the putty do I need to wait before painting?** Wait until strong enough skinning on top of glazing has formed, usually about 2-3 weeks for Dual Glaze and at least 14 days for TYPE M, depending on the temperature. Paint within 1 month of skin formation. Dual Glaze will not skin in shop. Take outdoors after application to cure.
- 6. Are there any recommendations regarding the kind of paint to use?** Use any good quality acrylic-latex or oil-based paint.
- 7. At what temperature can I apply the putty?** It is best to apply it above freezing. Do not apply it to damp or frosty wood. It can be applied below freezing as long as it can be worked.
- 8. Can curing time be accelerated?** No. However, warmer temperatures cause faster cure.
- 9. Can TYPE M be applied outdoors?** No. TYPE M hardens too quickly outdoors. Use indoors only.
- 10. What is the shelf-life?** The shelf life is indefinite if stored in cool place. If separation occurs, mix by hand. Cover unused putty in opened containers with plastic to prevent skin formation.

Rev.
06/13/16