



TREAD SPREAD™

Slip-Resistant Epoxy Coating

Help Prevent Slip and Fall Accidents with TREAD SPREAD™

Bonds tenaciously to concrete, wood, metal, fiberglass, and most rigid surfaces. Exceptional performance on wet, dry, and underwater surfaces. High-traction and easy to apply. Much more durable and long-lasting than tapes. Exceeds OSHA and ADA recommendations for slip resistance in both wet and dry conditions.

Applications: Pools, decks, locker rooms, boats, steps, ramps, loading docks, and other surfaces where slip resistance is needed.




Follow these easy instructions for a long-lasting application:

1. Apply tape to create stencil.




2. Mix together equal volumes of TREAD SPREAD Part A and B.



3. Apply with trowel or putty knife.



4. Remove tape before hardening.



TREAD SPREAD™

Slip-Resistant Epoxy Coating



Applications:

Tread Spread is a spreadable epoxy coating that includes a slip-resistant aggregate. It bonds tenaciously to concrete, wood, metal, fiberglass and most rigid surfaces. Provides high-traction and is easy to apply. Much more durable and long lasting than tapes. Tread Spread exceeds OSHA and ADA recommendations for slip resistance in both wet and dry conditions.

Features and Benefits:

- Reduce slips and falls
- Excellent performance on wet, dry, and underwater surfaces
- High traction
- Spreadable
- Extremely durable
- Easy to mix and apply
- Exceptional bond strength
- Available in Slate Gray, Safety Yellow, and Pool Blue

Packaging:

- 2 Pint Kit
- 2 Quart Kit
- 2 Gallon Kit

Technical Characteristics:

- Weight/gallon: 12.5; Kg/L: 1.5
- Coverage: 24 sq. ft./gallon x .10 inch thick; 284 linear ft. 1 inch wide x .10 inch thick.
- Pot life: 20-40 minutes at 77°F
- Hardening time: 1-1.5 hours at 75°F
- Slip-Resistance (American Slip Resistance Meter): 0.8
- Color: Slate Gray, Safety Yellow, and Pool Blue
- 100% Solids
- Pull-off Strength (ASTM 4541): 300 psi
- Hardness Shore D: 70
- Tensile Strength (ASTM D 638): 711 psi
- Flexural Strength (ASTM D 790): 1,295 psi
- Compressive Strength (ASTM D 695): 2,531 psi
- Elongation (ASTM D 638): 4.0%
- Viscosity, cps (ASTM D 652): 80,000-130,000

**The above information is based upon laboratory testing. Users are urged to test the product under their own conditions.*

Instructions:

- Surfaces must be clean and dry. Contaminants, oils, grease, old paint, stains and debris must be removed.
- Apply tape to create a stencil.
- Mix equal volumes of Tread Spread Part A and B.
- Apply with a trowel or putty knife.
- Remove tape before hardening.

Product Support:

Technical assistance is available by phone at 262-653-2000, by fax at 262-653-2019 or through the company website, www.abatron.com.

LIMITED WARRANTY: As uses and applications of this product are beyond the control of the manufacturer, all warranties, including the implied warranties of merchantability and fitness for a particular purpose, are excluded. In the event of manufacturing defects in the product, purchasers' remedies are limited to the replacement of the product or a refund of its purchase price. Liability for consequential damages is expressly excluded.

WARNING: IRRITANT.
KEEP OUT OF REACH OF CHILDREN.
Read statement on container before using.

Manufactured by:



Kenosha, WI • A Division of U.C Coatings, LLC • 800-445-1754 • www.abatron.com

Made in the USA ISO 9001 Registered